

M: H

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08J 11/00 // C09D 5/03		A1	(11) International Publication Number: WO 00/15705
			(43) International Publication Date: 23 March 2000 (23.03.00)
(21) International Application Number: PCT/GB99/03072		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 15 September 1999 (15.09.99)		Published <i>With international search report</i>	
(30) Priority Data: 9820089.2 16 September 1998 (16.09.98) GB			
(71) Applicant (for all designated States except US): PROTON POWDER COATINGS LIMITED [GB/GB]; Triumph Trading Park, Vitesse Avenue, Speke Hall Road, Liverpool L24 9GQ (GB).			
(72) Inventor; and			
(75) Inventor/Applicant (for US only): KILNER, Ian [GB/GB], Triumph Trading Park, Vitesse Avenue, Speke Hall Road, Liverpool L24 9GQ (GB).			
(74) Agent: THOMSON, Paul; Potts, Kerr & Co., 15 Hamilton Square, Birkenhead, Merseyside CH41 6BR (GB).			
(54) Title: A PROCESS FOR RECYCLING POWDER COATING FINES			
(57) Abstract <p>The present invention provides a process for recycling fines produced during the production of powder coatings comprising the steps of heating the fines for a sufficient time and a sufficient temperature such that a reusable product is obtained, cooling such product, crushing the cooled product to produce particles of a desired particle size; and removing any particles which are not of desired particle size.</p>			